

ROTTERDAM

Water Repellent

SESTAVA TKANINE COMPOSITION SIROVINSKI SASTAV TKANINE ZUSAMMENSETZUNG COMPOSIZIONE TESSUTO		100% POLIESTER 100% POLYESTER 100% POLIESTER 100% POLYESTER 100% POLIESTERE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	140 cm +/-2%	TEŽA WEIGHT TEŽINA GEWICHT PESO	480 g/m ² +/-5%
TEST	STANDARD	REZULTAT / RESULTS / REZULTAT / ERGEBNIS / RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE / ORDITO	VOTEK / WEFT / POTKA / SCHUSS / TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	804 N	1031 N
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	67 N	75,1 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA	EN ISO 13936-2	1 mm	1 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTÄNDIGKEIT RESISTENZA ALL'ABRASIONE	EN ISO 12947-2	>100.000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING	EN ISO 12945-2	2000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI	5000 OBRATOV / REVS. / OBRTAJA / TOUREN / GIRI
		5	5
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02	4	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORE ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		4-5	4-5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB B 82.02-2 & 82.02-15 DIN EN 14362-1 DIN EN 14362-3	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALLERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DI COLORANTI ALLERGENICI	DIN 54231	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
FORMALDEHID FORMALDEHYDE FORMALDEHID FORMALDEHYD FORMALDEIDE	EN ISO 14184-1	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	DIN EN 1021-1 BS 5852 Source 0	PRESTAL TEST PASSED PROŠAO TEST UEBERSTANDEN SUPERATO	
ZAŠČITA TKANINE FABRIC PROTECTION ZAŠTITA TKANINE STOFFSCHUTZ PROTEZIONE TESSUTO		VODOODBOJNI NANOS WATER REPELLENT VODOODBOJNI NANOS WASSERABWEISEND IDROPEPELENTE	

MED BARVNIMI PARTIJAMI SO MOŽNA ODSTOPANJA V BARVI. // COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE. //
MOGUČA SU ODSTUPANJA U BOJI KOD PROIZVODNJE. // FARBUNTERSCHIEDE ZWISCHEN FARBPARTIEN SIND MÖGLICH. //
TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.



MERCIS

fabrics and leathers



Rotterdam 03



Rotterdam 04



Rotterdam 13



Rotterdam 14



Rotterdam 16



Rotterdam 17



Rotterdam 24



Rotterdam 26



Rotterdam 27



Rotterdam 34



Rotterdam 36



Rotterdam 37



Rotterdam 38



Rotterdam 39



Rotterdam 43



Rotterdam 44



Rotterdam 46



Rotterdam 47



Rotterdam 49



Rotterdam 54



Rotterdam 56



Rotterdam 58



Rotterdam 64




Rotterdam 65



Rotterdam 74



Rotterdam 78



Rotterdam 84